




TYPE	Dimensions(mm)							
	A	B min	C1	C2	D	E min	F	H
EPC10	10.2 ± 0.2	7.6	5.0 ± 0.1	1.9 ± 0.1	4.05 ± 0.1	5.3	3.4 ± 0.1	2.65 ± 0.1
EPC13	13.3 ± 0.3	10.5	5.6 ± 0.15	2.05 ± 0.1	6.6 ± 0.2	8.3	4.6 ± 0.15	4.5 ± 0.2
EPC17	17.6 ± 0.38	14.3	7.7 ± 0.15	2.8 ± 0.1	8.55 ± 0.2	11.5	6.0 ± 0.15	6.05 ± 0.2
EPC19	19.1 ± 0.48	15.8	8.5 ± 0.15	2.5 ± 0.1	9.75 ± 0.2	13.1	6.0 ± 0.15	7.25 ± 0.2
EPC25	25.1 ± 0.5	20.65	11.5 ± 0.2	4.0 ± 0.1	12.5 ± 0.2	17.1	8.0 ± 0.2	9.0 ± 0.3
EPC27	27.1 ± 0.05	21.6	13.0 ± 0.3	4.0 ± 0.1	16.0 ± 0.2	18.5	8.0 ± 0.2	12.0 ± 0.3
EPC30	30.1 ± 0.5	23.6	15.0 ± 0.3	4.0 ± 0.1	17.5 ± 0.2	20.0	8.0 ± 0.2	13.0 ± 0.3

TYPE	C <sub>1</sub> (mm <sup>-1</sup> )	A <sub>e</sub> (mm <sup>2</sup> )	L <sub>e</sub> (mm)	V <sub>e</sub> (mm <sup>2</sup> )	AL(nH/N <sup>2</sup> ) ± 25%		Weight (g)
					TP3	TP4	
EPC10	1.89	9.39	17.8	167		1000	1.1
EPC13	2.46	12.5	30.6	382		827	2.1
EPC17	1.76	22.8	40.2	917		1150	4.5
EPC19	2.03	22.7	46.1	1047		940	5.3
EPC25	1.28	46.4	59.2	2748		1560	13
EPC27	1.34	54.6	73.1	3995		1540	18
EPC30	1.32	61.0	81.6	5035		1570	23



TYPE	Dimensions(mm)					
	A	B	C	D	E	F
EP7	$9.2 \pm 0.2$	$3.7 \pm 0.2$	$3.4^{+0}_{-0.2}$	$6.6^{+0}_{-0.4}$	$7.6^{+0}_{-0.4}$	$2.5^{+0.4}_{-0}$
EP10	$11.5 \pm 0.3$	$5.1 \pm 0.2$	$3.3 \pm 0.2$	$7.9^{+0}_{-0.4}$	$9.6^{+0}_{-0.4}$	$3.6^{+0.4}_{-0}$
EP13	$12.5 \pm 0.3$	$6.5 \pm 0.3$	$4.4 \pm 0.2$	$9.0^{+0}_{-0.4}$	$10.0 \pm 0.3$	$4.5^{+0.4}_{-0}$
EP17	$18.0 \pm 0.4$	$8.4 \pm 0.4$	$5.9^{+0}_{-0.4}$	$11.3^{+0}_{-0.6}$	$12.0 \pm 0.4$	$5.5^{+0.4}_{-0}$
EP20	$24 \pm 0.5$	$10.7 \pm 0.2$	$8.8 \pm 0.3$	$15.0 \pm 0.4$	$16.5 \pm 0.4$	$7.0^{+0.4}_{-0}$

TYPE	C <sub>i</sub> (mm <sup>-1</sup> )	A <sub>e</sub> (mm <sup>2</sup> )	L <sub>e</sub> (mm)	V <sub>e</sub> (mm <sup>2</sup> )	AL(nH/N <sup>2</sup> ) ± 25%		Weight (g)
					TP3	TP4	
EP7	1.52	10.3	15.7	163	880min	830min	1.4
EP10	1.7	11.3	19.2	218	850min	800min	2.8
EP13	1.24	19.6	24.2	476	1250min	1170min	4.9
EP17	0.84	33.9	28.5	966	1950min	1840min	11.8
EP20	0.508	79	39.8	3120	3450min	3200min	28



TYPE	Dimensions(mm)						
	A	B	C	D	E	F	G
EFD15	15.0 ± 0.4	7.5 ± .15	4.65 ± 0.15	5.3 ± 0.15	11.0 ± 0.35	5.5 ± 0.25	2.4 ± 0.1
EFD20	20.0 ± 0.55	10.0 ± 0.25	6.65 <sup>+0.2</sup> <sub>-0.15</sub>	8.9 ± 0.2	15.4 ± 0.5	7.7 ± 0.25	3.6 ± 0.2
EFD25	25.0 ± 0.65	12.5 ± 0.25	9.1 ± 0.2	11.4 ± 0.2	18.7 ± 0.6	9.3 ± 0.25	5.4 ± 0.25
EFD30	30.0 ± 0.8	15.0 ± 0.25	9.1 ± 0.3	14.6 ± 0.3	22.4 ± 0.75	11.2 ± 0.3	4.9 ± 0.15

TYPE	C <sub>i</sub> (mm <sup>-1</sup> )	A <sub>e</sub> (mm <sup>2</sup> )	L <sub>e</sub> (mm)	V <sub>e</sub> (mm <sup>2</sup> )	AL(nH/N <sup>2</sup> ) ± 25%		Weight (g)
					TP3	TP4	
EFD15	2.27	15	34	510		780	6.8
EFD20	1.52	31.0	47.0	1460		1200	7.4
EFD25	1.0	58.0	57.0	3300	2000	1800	16.6
EFD30	0.985	69.0	68.0	4700	2050	2050	24